



NUMBER: STH0709021

APPLICANT: BETA TEXTILES CO., LIMITED
6E, FUGANG MANSION, NO.36 RENMIN
ROAD(M), ZHANGJIAGANG, JIANGSU, CHINA
ATTN: DAVID SUN

DATE: MAR 26, 2007

SAMPLE DESCRIPTION:

ONE (1) SUBMITTED SAMPLES SAID TO BE **86% POLYESTER 14% SPANDEX KNITTED FABRIC IN BLACK.**

END USES: GARMENTS.

MANUFACTURER: BETA.

SAMPLE RECEIVED CONDITION: SAMPLE IN CLOSED PLASTIC BAG.

TESTS CONDUCTED:

AS REQUESTED BY THE APPLICANT, FOR DETAILS REFER TO ATTACHED PAGE(S)


COMMENT:

TESTED SAMPLE	ANTIBACTERIAL ACTIVITY (AATCC-147)	RESULT
FACE SURFACE OF SUBMITTED SAMPLE	AGAINST STAPHYLOCOCCUS AUREUS	ACCEPTABLE
	AGAINST KLEBSIELLA PNEUMONIAE	ACCEPTABLE

TO BE CONTINUED

PREPARED AND CHECKED BY:
FOR INTERTEK TESTING SERVICES
LTD., SHANGHAI

JAMES WANG
GENERAL MANAGER



NUMBER: STH0709021

ANTIBACTERIAL ACTIVITY TEST-PARALLEL STREAK METHOD (QUALITATIVE)

WITH REFERENCE TO 2006 AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS, TECHNICAL MANUAL, AATCC TEST METHOD 147-2004.

ULTRAVIOLET STERILIZATION OF SAMPLE BEFORE TEST.

INCUBATION TEMPERATURE : 37 .

INCUBATION PERIOD : 18 - 24 HOURS.

AGAR MEDIUM: NUTRIENT AGAR.

TEST CULTURE : *STAPHYLOCOCCUS AUREUS* (ATCC 6538).
KLEBSIELLA PNEUMONIAE (ATCC 4352).

TEST SPECIMEN : 25 × 50mm / RECTANGULAR / FACE SURFACE OF SUBMITTED SAMPLE.

RESULT :

TEST MICROORGANISM	RESULT
<u>STAPHYLOCOCCUS AUREUS</u>	NO GROWTH WAS OBSERVED DIRECTLY UNDERNEATH THE TESTED SPECIMEN WITH * CLEAR ZONE 0 mm.
<u>KLEBSIELLA PNEUMONIAE</u>	NO GROWTH WAS OBSERVED DIRECTLY UNDERNEATH THE TESTED SPECIMEN WITH * CLEAR ZONE 0 mm.

REMARK: * = WIDTH OF CLEAR ZONE OF INHIBITION BELONG THE EDGE OF THE TESTED SPECIMEN.

THIS TEST WAS CONDUCTED BY INTERTEK TESTING SERVICES HONGKONG LTD.

DATE SAMPLE RECEIVED : MAR.16, 2007

TESTING PERIOD : MAR.20, 2007 TO MAR.22, 2007

END OF REPORT